





Spotted Gum

Botanical Name: *Eucalyptus Maculata*

Spotted Gum has a wide range of colours depending on the location of the source forest. Ranging from light brown through definite browns to deep red-brown hues. It can also have patches of white to light brown colours running through it up to 50mm wide. Spotted Gum is a moderately coarse and uneven textured wood with some timbers having the additional feature of a wavy grain, giving rise to an attractive fiddleback figure.

Typical Characteristics



Origin New South Wales and Queensland

Species Type Hardwood

Sustainability **ON REQUEST ONLY.**
Available in PEFC 21-31-167 with a Chain of Custody for Green Star points.

Availability Readily available

Durability Class 1 – greater than 40 years

Hardness Janka 11

Density (dry) 990kg/m³

Movement Medium tangential 6.1%
(shrinkage across the board width)

Treatment ACQH3

Lyctid Susceptibility Susceptible

Termite Resistance Resistant

Fire Satisfies BAL 12.5, 19 and 29 under AS3959-2009. Satisfies BCA C1.10a Group 3

Lengths Average length 2.4m
(this can vary depending on availability)

Typical Applications Internal cladding and battens
External cladding and battens



sculptform.com | support@sculptform.com

REFERENCES: Wood Solutions (www.woodsolutions.com.au); Australian Standards AS5604-2005; Wood in Australia by Keith R. Bootle 2002 ISBN 0 07 451047 9.; Australian Standards AS 3959-2009

NOTE: To maintain currency, this document is periodically reviewed, and new editions are published. Between editions, amendments may be issued, so it's important that readers assure themselves they are using a current document. We welcome suggestions for improvement, and encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email support@sculptform.com

On request only.
Available in
PEFC/Responsible
Wood with a Chain
of Custody for
Green Star points.

