



BLACKBUTT

ORIGIN	New South Wales and Queensland
SPECIES TYPE	Hardwood
SUSTAINABILITY	Available in PEFC/AFS with a Chain of Custody for Green Star points. On request only.
AVAILABILITY	Readily available
DURABILITY	Class 1 out of ground (40 years +)
HARDNESS	Janka 9.1kN
DENSITY (DRY)	880kg/m ³ (at 12% moisture content)
MOVEMENT	High tangential 7.3% (shrinkage across the board width)
LYCTID SUSCEPTIBILITY	Not susceptible
TERMITE RESISTANCE	Resistant
FIRE	Satisfies BCA C1.10a Group 3 (slightly combustible) and BAL 12.5, 19 and 29 under AS3959-2009. Ignitibility: 13, Spread of Flame Index: 7, Smoke Developed Index: 3, Critical Radiance Flux Higher and Lower: >2.2 and 4.5kW/m ² , Smoke Development Rate: <750, Average Extinction Area: <250
LENGTHS	Average length 2.0m - 2.4m
TYPICAL APPLICATIONS	Internal cladding and battens External cladding and battens

BOTANICAL NAME: EUCALYPTUS PILULARIS

Blackbutt has an even texture. The grain can be interlocked but it is generally straight, making it appealing for interior use. It ranges from golden yellow to pale brown, although occasionally a slight pinkish colour may be present. Small gum veins are common.

TYPICAL CHARACTERISTICS



January 2016 | 01290116



1800 008 828
sculptform.com.au | support@sculptform.com.au

REFERENCES: Wood Solutions (www.woodsolutions.com.au); Australian Standards AS5604-2005; Wood in Australia by Keith R. Bootle 2002 ISBN 0 07 451047 9.; Australian Standards AS 3959-2009

NOTE: To maintain currency, this document is periodically reviewed, and new editions are published. Between editions, amendments may be issued, so its important that readers assure themselves they are using a current document. We welcome suggestions for improvement, and encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email support@sculptform.com.au or phone 1800 008 828.

Available in PEFC/
Responsible Wood with
a Chain of Custody for
Green Star points. On
request only.

