





# WHITE OAK

ORIGIN	North America
SPECIES TYPE	Hardwood
SUSTAINABILITY	Available in FSC® with a Chain of Custody for Green Star points. On request only.
AVAILABILITY	Readily available
DURABILITY	Recommended for interior use only.
HARDNESS	Janka 6kN
DENSITY (DRY)	755kg/m³
MOVEMENT	Medium tangential 5% (shrinkage across the board width)
LYCTID SUSCEPTIBILITY	Susceptible
TERMITE RESISTANCE	Not resistant
FIRE	Satisfies BCA C1.10a Group 3
LENGTHS	Average length 2.0m - 2.2m (this can vary depending on availability)
TYPICAL APPLICATIONS	Internal cladding and battens

## BOTANICAL NAME: QUERCAS ALBA

American White Oak is pale yellow-brown to mid-brown, sometimes with a pink tinge. It is mostly straight grained with a medium to coarse texture, and with longer rays and more figure than Red Oak. It has large distinctive growth rings and some medullary rays may be present.

### TYPICAL CHARACTERISTICS



January 2016 | 01290116



1800 008 828  
sculptform.com.au | support@sculptform.com.au

REFERENCES: Wood Solutions ([www.woodsolutions.com.au](http://www.woodsolutions.com.au)); Australian Standards AS5604-2005; Wood in Australia by Keith R. Bootle 2002 ISBN 0 07 451047 9.; Australian Standards AS 3959-2009

NOTE: To maintain currency, this document is periodically reviewed, and new editions are published. Between editions, amendments may be issued, so its important that readers assure themselves they are using a current document. We welcome suggestions for improvement, and encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email [support@sculptform.com.au](mailto:support@sculptform.com.au) or phone 1800 008 828.

Available in FSC®  
with a Chain of  
Custody for Green  
Star points. On  
request only.



The mark of  
responsible forestry